

Two-sided contact adhesive

Basis	Synthetic rubber in solvent.
Colour	Cream.
Consistency	Thick liquid.

Product advantages:

- High initial adhesion strength
- Fast drying
- High final bond strength
- Favourable spreading capacity

Application

For the two-sided installation of:

- rubber
- homogeneous PVC
- plastic profiles
- linoleum
- leather, board, cork
- carpet
- foam-rubber.

Working Process

Waiting time	15 Minutes.*
Open time	1 Hour.*
Drying time	12 Hours.*
Tools	Adhesive spreader A4 or brush.
Storage	Protect against high temperatures.
Shelf life	6 Months, in unopened packaging.

* The mentioned values have been established in our laboratory and must be considered as guidelines in view of possible variations in climatic circumstances, subfloor compositions and layer thickness.

Subfloor:

- 233 Eurosol Contact is suitable for any type of subfloor that has a good tensile and compression strength. The subfloor should also be clean, permanently dry and free from grease and dirt, according to the requirements of BS 8203 or DIN 18 365.
- In advance always seek our technical data sheets. In doubt about the application ask for technical advice.

Working conditions:

Required surrounding temperature : 18° C - 23° C.
Material and subfloor temperature : min. 15° C - max. 20° C.
Relative humidity : 40-80%.

233 eurosol contact

Directions for use

- Shake the adhesive well before use.
- Apply the adhesive on the subfloor and back of the material to be fixed with a brush or adhesive spreader A2.
- Allow the adhesive to dry for 15 minutes (depending on temperature, relative humidity, subfloor and material).
- Place the material on the subfloor and press, roll or hammer firmly.
- After mixing adjustments are not longer possible.
- Remove fresh spots immediately with white spirit.
- Do not smoke during application, do not expose to naked flame, extinguish pilot lights and ventilate thoroughly.

Underfloor heating systems:

233 Eurosol Contact can be applied on underfloor heating systems. Turn off the heater 24 hours before application. Do not heat again until at least 24 hours after installation, in steps of 5° C per day.

Packaging

10 metal drum.

OUR DIRECTIONS FOR USE ARE BASED ON ACCURATE LABORATORY TESTS AND EXTENSIVE PRACTICAL EXPERIENCES. HOWEVER, WE CANNOT TAKE RESPONSIBILITY FOR EXECUTED WORK AND THEREFORE WE ADVISE YOU TO MAKE TESTS AT THE PLACE OF WORK. OTHERWISE WE REFER TO OUR GENERAL SALES CONDITIONS.

