



	PRODUCT CHARACTERISTICS			
	Standard	Requirement	Unit	Results
PRODUCT DESCRIPTION				
Surface treatment	-	-	-	Protectsol
Surface complex	-	-	-	D-Max
Foam	-	-	-	CXP HD
Thickness	EN 428	-	mm	12 mm
Weight	EN 430	-	kg/m ²	5,1
Length	EN 426	-	lm	26.4 max
Width	EN 426	-	lm	1,5
Impact Protection Index	AC- P90-205	-	%	IPI = 88%
SPORT PROPERTIES				
Shock absorption	EN 14808	≥ 25	%	P3
Vertical deformation	EN 14809	≤ 3.5	mm	≤ 3.5
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
CLASSIFICATION				
Fire	EN 13501-1	-	-	C_{fl}-s1
Anti-bacterial activity (E. coli - S. aureus - MRSA) (3)	ISO 22196	-	-	> 99% inhibits growth
DECLARATION OF PERFORMANCE				
CE	DOP n°xxx	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to rolling load

	INSTALLATION METHODS		
	Gerflor's recommendation	Unit	Results
Taraflex™ Sport M Comfort specific installation method	Level of dampness of the subfloor	%	No limit (no dripping water on the slab)

COLOUR RANGE

TARAFLEX™ SPORT M COMFORT

Standard roll 20.5
○ ml

(3) The implementation of an effective cleaning method is the best defence against infection